

EverSolv 360 has been lab-tested for compatibility with the materials below:

Material	EverSolv 360 Compatibility
ABS	Very Good
Aluminum	Excellent
Buna N	Excellent
Brass	Excellent
Bronze	Excellent
Ceramic	Excellent
Carbon/Graphite	Excellent
Carpenter 20	Excellent
Cast bronze	Excellent
Ceramagnet A	Excellent
Copper	Very Good
CPVC	Excellent
Cycolac™ (ABS)	Good
Epoxy	Excellent
Fiberglass	Very Good
Fluro-Silicone	Excellent
Hastelloy C	Excellent
Kynar™	Excellent

Material	EverSolv 360 Compatibility
Neoprene	Excellent
Nitrile	Excellent
Noryl	Very Good
Nylon	Excellent
Phenolic	Excellent
Polycarbonate	Very Good
Polyurethane	Very Good
PVC	Good
Stainless Steel (304)	Excellent
Stainless Steel (316)	Excellent
Stainless Steel (440)	Excellent
Styrene/Polystyrene	Not recommended
Steel, Mild or Carbon	Excellent
Teflon™	Excellent
Titanium	Excellent
Tygon™	Not recommended
Viton™	Excellent

To simulate long term storage compatibility, these materials were soaked in EverSolv 360 in a controlled 150°F environment for two weeks.

Please review the EverSolv 360 SDS and do not handle until all safety precautions have been read and understood.

To learn more about EverSolv 360, please contact your BioChem representative for more information.



A WHOLLY OWNED
SUBSIDIARY OF
REFINED
technologies



Replacing hazardous solvents without compromising effectiveness.

BioChem Systems
480 Wildwood Forest • Suite 400
Spring, Texas 77380
cservice@biochemsys.com
800-777-7870